

Use Millefiori to Accent Your Ceramic Art



Artist: Genna White

Delphi experts have discovered that 90 COE Millefiori can be added as a colorful, dimensional accent to glazed ceramics. Simply place millefiori on a flat or moderately sloped surface for a second firing following the recommended schedule* listed below. (Select the firing schedule for your glass or ceramic kiln.)

Glass Kiln:

300° F per hour to 1320° F

Hold for 5 minutes

Allow kiln to cool to room temperature on its own.

Ceramic Kiln:

Cone 018

Medium Speed

Hold for 5 minutes

Allow kiln to cool to room temperature on its own.

* Firing times and temperatures may vary, each kiln is unique.



Delphi Tip

Use Glastac #B8234 to keep millefiori in place until a heat bond has been established.



DELPHI
Be Creative!

DelphiGlass.com • info@delphiglass.com
To Order **800-248-2048**
Project Help Line **800-821-9450**